

**High Gold Content Alloy**  
for low-fusing high-expanding ceramics  
free of palladium, silver and copper

**PLATINOR® AM 97**

acc. to DIN EN ISO 9693  
acc. to DIN EN ISO 22674

Item no. 7344 3 001  
Delivery form Casting plates  
Indication Classic ceramic,  
inlays, onlays, crown technique  
longer span bridges

QM-System certified  
according to DIN EN ISO 13485  
for medical products



**Alloy: Au 87 Pt 10**

Type	Colour	Density g/cm <sup>3</sup>	Composition content in % (m/m)										
			Au + Pt metals	Au	Pt	Ir	In						
-	yellow	18.6	97.0	87.0	9.9	0.1	3.0						

The alloy is free of Ni, Co, Cr, Be, Cd.

**Technical data**

Vickers hardness HV 5/30			0.2 % proof stress MPa		Elongation %		Modulus of elasticity MPa	Average linear CTE µm/m · K		Melting range °C	Preheating temp. °C	Casting temp. °C	Annealing °C min	Hardening °C min
g	n	a	n	a	n	a		25-500 °C	25-600 °C					
125	140	180	385	495	12	8	86.000	14.3	14.5	1000-1135	800	1290	- -	500 15

g = after casting, n = after firing, a = hardened

**Solders**

Application	Solder	Working temp. °C	Composition content in % (m/m) (x=<0.1%)							Colour	
			Au	Pt	Ir	Ag	Zn	Cu	In		
Primary solder/ before firing	PLATINOR® APF-Lot	1010	62.0	1.0	x	36.0		0.5	0.5		yellow
Secondary solder/ after firing	PLATINOR® CPF-Lot 2	710	73.0	0.5	x	12.5	14.0	-	-		yellow

**Instruction for use**

## Instruction for use PLATINOR® AM 97

### 1. Modelling

Create an anatomically reduced wax model, considering the planned veneering. Sharp edges are to be avoided, soft level crossings are to be striven at.

Due to stability reasons, care has to be taken at bridge frames to achieve solid modulation of the connections and in the case of larger spans to create palatal and interdental strength of the connecting parts. Wall thickness of the modelled (waxed) single crowns at least 0.4 (0.3) mm, bridge pillar crowns at least 0.5 (0.4) mm.

### 2. Spruing System

Single crown:

Direct spruing with casting channel at least Ø 3.5 mm

From 2 single crowns on and bridges:

Running bars or rings with

object spruing 3.0 x 3.0 mm

running bars/rings Ø 4.0 – Ø 5.0 mm

casting channels Ø 3.5 – Ø 4.0 mm

### 3. Position of the Wax Model in the Investment Mould

Distance from the mould wall: The units should have at least 5-10 mm distance from the mould wall.

Distance from the mould bottom: Direct spruing between wax units and mould bottom a distance of 10 – 15 mm has to be kept.

Investment of running bars or rings: the middle of the running bar or ring should cover the middle of the mould.

### 4. Investment

Cover investment mould with investment ring spacer.

Investment mould x 1 / x 3: 1 layer

Investment mould x 6 / x 9: 1 – 2 layers

Phosphate bonded investment material is required.

The investment material manufacturer's instructions for use have to be complied with strictly.

### 5. Burnout / Preheating

Burnout immediately after drying of the investment material at 280-300 °C according to the mould size respectively 30/40/50/60 min. Preheating at 800 °C according to the mould size respectively for 20/30/40/50/60 min. If handling a greater number of moulds, the preheating time has to be extended accordingly. The preheating time is specific to the alloy and must be observed.

### 6. Crucible Material

Ceramic and graphite crucibles can be used.

### 7. Casting Units

All common melting and casting units can be used.

### 8. Casting

Casting temperature at 1290 °C

Further heating times after reaching the liquidus temperature according to the quantity of material used and unit output.

Resistance heating 60 – 120 sec.

High frequency 5 – 10 sec.

Propane / Oxygen torch 5 – 10 sec.

In the case of torch melting, pay attention to the correct setting of the torch (danger of carbon damage) and melt with the reduced zone.

### 9. Casting Residues

In order to preserve the alloy characteristics and the casting quality, no more than 50 % cleaned casting residues should be used.

The weight used is calculated from: wax weight x alloy density (see Heimerle + Meule calculation sheet).

### 10. Cooling and Divestment

Let mould cool down below room temperature to hand temperature and carefully divest.

This avoids deviations in fitting, change of alloy characteristics, and hot fissures. Sandblast with high grade corundum (approx. 100 µm) or with an market pickling agent to remove the investment material.

### 11. Finishing and Cleaning

Finish frame with tungsten carbide burs and ceramic bonded milling tools with only little pressure; then sandblast surface with aluminium oxide (approx. 100 µm) at low pressure ( max.2 bar). Then steamclean the frame and degrease it with a suitable pickling agent (e.g. AMISUL). During grinding sufficient protection against dust inhalation has to be taken.

### 12. Oxidation

10 min. at 950 °C with vacuum.

If the oxide layer shows spots, grind the frame again and repeat the work steps. Thereafter steamclean the frame and degrease it with a suitable pickling agent (e.g. AMISUL).

### 13. Firing of the Ceramic

The alloy is suited for conventional ceramics, max. firing temperature 950 °C

Compatible ceramics:

Omega 900, VMK 95, Omega, Creation, Duceram Plus, Carat.

With regard to the firing cycles the indications of the respective ceramic manufacturer have to be complied with strictly.

### 14. Firing Process

After each firing cycle the object has to be cooled down at a middle speed according to the CTE of 14.5 µm/m – K. Ensure a safe support of the frame by firing pins or casted loops/pins; otherwise individual firing pins (fireproof stump material) are to be used.

### 15. Soldering

Soldering areas have to be sufficiently big and should already be considered during modelling.

Soldering areas have to be metallically blank.

The solder gap should be 0.05 – 0.2 mm.

Recommended flux material: Universal soldering paste ARGOFLEX

Solder before firing: PLATINOR® APF-Lot 1010 °C

Solders after firing: PLATINOR® CPF-Lot 1 710 °C

Slowly cool down the soldering object.

### 16. Hardening

After casting / firing PLATINOR AM 97 shows a sufficiently high density for its area of indication. If required, the maximum hardening can be reached by a final annealing at 500 °C for 15 min.

### 17. Pickling and Polishing

Remove flux residues or oxides by pickling in AMISUL at about 80 °C or by sandblasting. Rubber-wheel the frame; final polishing can be accomplished with pastes, brushes, buffing wheels, and felt.