

<b>Heimerle + Meule GmbH</b> Dennigstr. 16, D - 75179 Pforzheim Phone: + 49 (0) 7231-940-0 www.heimerle-meule.com	<b>Material data</b>	WKD – 115.585
		Date: 05/2014

<b>Alloy</b>	<b>Au 585</b>	
Item – no.	<b>115-585</b>	
Colour	light red	
Precious metals	Au 58,5 Ag 7,0	[%]
Density	13,2	[g/cm <sup>3</sup> ]
Melting range	870 - 940	[°C]

<b>Properties</b>	soft - annealed	
Annealing temperature	650	[°C]
Hardness	140	[HV]
Tensile strength	490	[MPa]
Yield point	310	[MPa]
Elongation	30	[%]

<b>Casting of jewellery</b>		
Flask temperature	approx. 600	[°C]
Casting temperature	1040 – 1140	[°C]
Hardness	140	[HV]

### Portrait of alloy

- Coloured gold alloy
- High ductility and forming capacity
- Good turning and casting characteristics
- Age – hardenable up to 165 HV: 350°C, 30 min, slow cooling down on air
- Excellent workability for jewellery fabrication
- Suitable to produce tubes and ring blanks for wedding rings
- Ring blanks, delivery hardness: approx. 160 HV