

Heimerle + Meule GmbH Dennigstr. 16, D - 75179 Pforzheim Phone: + 49 (0) 7231-940-0 www.heimerle-meule.com	Material data	WKD – 295.750
		Date: 05/2014

Alloy	L – Au750 W	
Item – no.	295-750	
Colour	yellow	
Precious metals	Au 75,0 Ag 10,0	[%]
Density	14,5	[g/cm ³]

Melting range	705 – 750	[°C]
Working temperature	approx. 750	[°C]

Portrait of the alloy

- Yellowgold brazing solder
- Cadmium free, nickel free
- Especially for brazing of 18K gold alloys