

Edelmetall-Legierungen | *Precious metal alloys*

Gusslegierungen von BEDRA DENT® | *Casting alloys from BEDRA DENT®*

	Farbe <i>Colour</i>	Au + Pt-Metalle in % <i>Au + Pt-Metals in %</i>	mittl. lin. WAK $\mu\text{m/mK}$ 25 - 500°C <i>CTE $\mu\text{m/mK}$ 25 - 500 °C</i>	Indikatoren <i>Indications</i>	Laserdraht 0,3/0,5 mm x 200 mm <i>Laser Welding \varnothing 0.3/0.5 mm x 200 mm</i>
BEDRA DENT® GL-1 BIO	gelb <i>yellow</i>	-	15,7	1,2,5,6,7	GL-1.4 BIO
BEDRA DENT® GL-1.4 BIO	gelb <i>yellow</i>	-	16,7	1,2,5,6,7	GL-1.4 BIO
BEDRA DENT® IL-50 BIO	sattgelb <i>dark yellow</i>	-	16,4	1,2	GL-2.6 BIO
BEDRA DENT® GL-2.6 BIO	gelb <i>yellow</i>	-	16,0	1,2,5,6,7	GL-2.6 BIO
BEDRA DENT® GL-2 BIO	gelb <i>yellow</i>	-	16,7	1,2,5,6,7	GL-2.6 BIO
BEDRA DENT® RGL-40	hellgelb <i>light yellow</i>	-	16,6	1,2,5,6,7	UL-40