

## Edelmetall-Legierungen | *Precious metal alloys*

Hochgoldhaltige Aufbrennlegierungen von BEDRA DENT® | *High-gold veneering alloys from BEDRA DENT®*

	Farbe <i>Colour</i>	Au + Pt-Metalle in % <i>Au + Pt-Metals in %</i>	mittl. lin. WAK $\mu\text{m}/\text{mK}$ 25 - 500°C <i>CTE <math>\mu\text{m}/\text{mK}</math> 25 - 500 °C</i>	Indikatoren <i>Indications</i>	Laserdraht 0,3/0,5 mm x 200 mm <i>Laser Welding <math>\varnothing</math> 0.3/0.5 mm x 200 mm</i>
BEDRA DENT® AL-3.4 BIO	gelb <i>yellow</i>	97,9	14,2	1,2,5,6	AL-3.4 BIO
BEDRA DENT® AL-3 BIO	gelb <i>yellow</i>	97,9	14,3	1,2,5,6	AL-3 BIO
BEDRA DENT® AL-3.6 BIO	sattgelb <i>dark yellow</i>	98,4	14,3	1,2,4,6	AL-3.6 BIO
BEDRA DENT® AL- 4 BIO	hellgelb <i>light yellow</i>	96,8	14,0	1,2,5,6,7	AL-3.6 BIO
BEDRA DENT® AL 5	weiß <i>white</i>	95,9	14,2	1,2,5,6,7	AL-3.6 BIO
BEDRA DENT® RAL-82	weiß <i>white</i>	90,5	13,9	2,5,6,7	
BEDRA DENT® ÖKO-2	hellgelb <i>light yellow</i>	62,0	14,8	1,2,5,6,7	ÖKO-2