

Edelmetall-Legierungen | *Precious metal alloys*

Universalliegierungen von BEDRA DENT® | *Universal alloys from BEDRA DENT®*

	Farbe <i>Colour</i>	Au + Pt-Metalle in % <i>Au + Pt-Metals in %</i>	mittl. lin. WAK $\mu\text{m}/\text{mK}$ 25 - 500°C <i>CTE $\mu\text{m}/\text{mK}$ 25 - 500 °C</i>	Indikatoren <i>Indications</i>	Laserdraht 0,3/0,5 mm x 200 mm <i>Laser Welding \varnothing 0.3/0.5 mm x 200 mm</i>
BEDRA DENT® UL-10 BIO	sattgelb <i>dark yellow</i>	85,4	15,7	1,2,5,6,7	UL-10 BIO
BEDRA DENT® UL-21	sattgelb <i>dark yellow</i>	82,9	16,7	1,2,5,6,7	UL-21
BEDRA DENT® U-15	gelb <i>yellow</i>	82,8	16,4	1,2,5,6,7	UL-21
BEDRA DENT® UL-12	gelb <i>yellow</i>	82,5	16,0	1,2,5,6,7	UL-10 BIO
BEDRA DENT® UL-40	hellgelb <i>light yellow</i>	67,1	16,7	1,2,5,6,7	UL-40
BEDRA DENT® ÖKO-1	hellgelb <i>light yellow</i>	49,0	16,6	1,2,5,6,7	ÖKO-1